

























# **Technical Specifications**

| _ |   |   |   |
|---|---|---|---|
| ς | i | 7 | S |

| Size          | Thickness | Wear Layer | Pcs/Carton | Sqft/Carton | Carton/Pallet | Sqft/Pallet | Lbs/Carton |
|---------------|-----------|------------|------------|-------------|---------------|-------------|------------|
| 6 in x 48 in  | 2.0 mm    | 12 mil     | 27 pcs     | 54 sqft     | 48 ctns       | 2592 sqft   | 35.24 lbs  |
| 12 in x 24 in | 2.0 mm    | 12 mil     | 22 pcs     | 44 sqft     | 60 ctns       | 2640 sqft   | 35.24 lbs  |

## **Testing**

| Test Item                               | Standard                              | Results                                |
|---|---------------------------------------|--|
| Level of use                            | ASTM F1700                            | Residential, Light Commercial          |
| Static load limit                       | ASTM F970                             | Passes, modified at 1000 psi           |
| Squareness, Straightness, and Thickness | ASTM F2421<br>ASTM F2055<br>ASTM F386 | Passes<br>Passes<br>Passes             |
| Flexibility                             | ASTM F137                             | Passes                                 |
| Dimensional stability                   | ASTM F2199                            | Passes                                 |
| Residual Indentation                    | ASTM F1914                            | Passes, Avg <8% max single reading 10% |
| Resistance to chemicals                 | ASTM F925                             | Passes, No defects                     |
| Resistance to light                     | ASTM F1515                            | Passes, E <8                           |
| Resistance to heat                      | ASTM F1514                            | Passes, E <8                           |
| Critical Radiant Flux                   | ASTM E648                             | Class 1 (>0.45 W/cm2)                  |
| Smoke density                           | ASTM E662                             | Part A, Less than 450                  |
| Indoor air quality                      |                                       | Low VOC, Floor Score certified         |
| Warranty                                |                                       | 10-yr Limited Light Commercial         |

#### Caution

Condition in at least 19°C (67°F) or the normal temperature of the room where the product is to be laid, for at least 48 hours before installing. Cartons must be stacked less than 5 high and planks/tiles removed 30 minutes before use. The site conditions must be maintained during installation and for at least 48 hours after completion. Evo Floors, LLC will not accept claims where these instructions have not been followed.

## Manufacturing

ISO 9001 Quality Management System
ISO 14001 Environmental Management System
OSHAS 18001 Occupational Health and Safety Management System

### Certification













































Leaders in Innovative Commercial Flooring!





























